



Markets

- Healthcare
- Education

Applications

- Medical / Acute Care
- Clinical / Labs
- Therapy / Rehab
- Common Areas
- K-12 / Higher Ed

Benefits

- PVC free
- Ergonomic; provides comfort underfoot
- Durable
- Hygienic because of heat-welded installation
- Lower in-room impact sound
- Excellent resistance to stains, scratches, and dirt
- High coefficient of friction
- Resistant to bacteria and fungi growth

Nada Rx features a 2mm Enomer® surface layer factory fusion bonded to a 5mm vulcanized composition rubber (VCR) base layer. Enomer® is an innovative flooring material free from PVC, plasticizers, phthalates, halogens, chlorines, and heavy metals. Designed for commercial spaces where safety, acoustic performance, ergonomic support, comfort under foot, and hygienic conditions are key, Nada Rx with heat-welded seams is easy-to-maintain, stain resistant, and performs in heavy traffic and load areas.

Product Information

Nominal Dimensions:

Available as a standard in rolls. Talk to your local agent to determine availability, pricing, minimums, and lead times.



Rolls:
57" (1.45m) x 30' (9.15m)
Thickness: 7 mm
(2 mm surface layer + 5 mm VCR base layer)

[View Colors](#)

THE NRG FACTOR

NRG

10.6%

Force Reduction

Absorption of impact energy

68.0%

Energy Restitution

Useful return of impact energy

Safety

Ergonomics

Acoustics

Technical Details

Performance Criteria	Test Standard	Typical Results
Recovery After Static Load	ASTM F970 ASTM F970 Modified	0.005" (@250 psi) 0.008" (@500 psi)
Coefficient of Friction	ASTM D2047	≥ 0.6
VOC Compliant	CA01350 / ASTM D5116	Pass
Flammability-Critical Radial Flux	ASTM E648	Class II
Abrasion Resistance	ASTM D3389	Pass
Resistance to Light	ASTM F1515	Pass
Resistance to Heat	ASTM F1514	Pass
Sound Transmission Class (STC)	ASTM E90	54
Impact Insulation Class (IIC)*	ASTM E492	54
Delta IIC*	ASTM E2179	23
Noise Reduction Coefficient (NRC)	ASTM C423	0.10

* Tested on a 6" concrete slab with no ceiling.

ecosurfaces.com • 833-888-1760

BUILT ON

itsTRU[®]

TECHNOLOGY

eco

surfaces